

nora® products for foot beddings

lift sheets and cushioning sheets



nora® Product information: nora® products for foot beddings

Overview of the nora® products for foot beddings
all sheets are available in different thicknesses, formats and colours

Function	Product	Hardness approx. Shore A	Density approx. g/cm ³	thermo- formable at approx.
<i>cushioning</i>	Astro form 8	-	0,20	110-130°
<i>cushioning</i>	Astro med 10	10	0,27	no
<i>cushioning</i>	Lunatec motion 10	10	0,13	110-130°
<i>cushioning</i>	Astro form 15	15	0,32	110-130°
<i>bedding/shockabsorbing</i>	Aero sorb W	-	0,15	110-130°
<i>bedding/shockabsorbing</i>	Aero sorb M	-	0,16	110-130°
<i>bedding</i>	Lunairmed	16	0,08	110-130°
<i>bedding</i>	Lunatur 18 Walnut	18	0,12	110-130°
<i>bedding</i>	Lunatec motion 20	20	0,18	110-130°
<i>bedding</i>	Lunairflex	22	0,12	110-130°
<i>permanently resilient</i>	Lunatec EP	22	0,20	110-130°
<i>permanently resilient</i>	Lunalastik	25	0,23	110-130°
<i>permanently resilient</i>	Lunatur 27 Walnut	27	0,24	110-130°
<i>permanently resilient</i>	Lunasoft SLW	30	0,20	130°
<i>stabilising</i>	Lunasoft SL	40	0,20	130°
<i>stabilising</i>	Lunatec SE	45	0,28	130°
<i>stabilising</i>	Lunasoft AL	52	0,26	130°
<i>stabilising</i>	Lunatur 50 Walnut	50	0,35	130°
<i>stabilising</i>	Lunalight A	58	0,35	130°
<i>stabilising</i>	Lunacell A	68	0,37	130°
<i>place holder</i>	Norit L	93	0,90	130°
<i>place holder</i>	Norit	95	1,05	130°

nora® products for foot beddings

composite sheets

Overview of the Lunatec combi composite sheets



Function: <i>cushioning</i>
Function: <i>bedding</i>
Function: <i>permanently resilient</i>
Function: <i>stabilising</i>

Product	Layers (thicknesses approx.)	Hardness approx. Shore A	Density approx. g/cm ³
Lunatec combi 1	Lunalastik (6 mm)	25	0,23
14 mm	Lunasoft AL (8 mm)	52	0,26
Lunatec combi 2	Lunairflex (6 mm)	22	0,12
16 mm	Lunasoft SLW (10 mm)	30	0,20
Lunatec combi 3	Lunalastik (6 mm)	25	0,23
16 mm	Lunasoft SLW (10 mm)	30	0,20
Lunatec combi 4	Lunairflex (3 mm)	22	0,12
9 mm	Lunalastik (6 mm)	25	0,23
Lunatec combi 5	Lunalastik (3 mm)	25	0,23
7 mm	Lunasoft SLW (4 mm)	30	0,20
Lunatec combi 6	Lunasoft SLW (4 mm)	30	0,20
14 mm	Lunasoft AL (10 mm)	52	0,26
Lunatec combi 7	Lunasoft SLW (3 mm)	30	0,20
7 mm	Lunasoft SL (4 mm)	40	0,20
Lunatec combi 8	Lunatec EP (4 mm)	22	0,20
12 mm	Lunatec SE (8 mm)	45	0,28
Lunatec combi cork 1	Lunalastik (6 mm)	25	0,23
14 mm	Lunatec cork H (8 mm)	50	0,35
Lunatur combi CW	Lunatur 27 Walnut (6 mm)	27	0,24
14 mm	Lunatec cork H (8 mm)	50	0,35
Lunatec combi motion	Lunatec motion (6 mm)	10	0,13
16 mm	Lunasoft SL (10 mm)	40	0,20
Lunatec combi T1	Lunasoft SLW (3 mm)	30	0,20
15 mm	Lunasoft Z (4 mm)	25	0,17
	Lunasoft AL (8 mm)	52	0,26